






## PP Grades

Grade	MFI (g / 10 min)	Density (g / cm <sup>3</sup> )	Additives	Applications
 <b>PPB200</b>	0,55	0,91	B	Extrusion for pipes, sheets and blow moulding for bottles
 <b>PPB300</b>	0,85	0,91	B	Extrusion for pipes, sheets and blow moulding for bottles

## HDPE Grades

Grade	MFI (g / 10 min)	Density (g / cm <sup>3</sup> )	Additives	Applications
 <b>HDPE5205B</b>	0,25	0,95	B	Blow moulding, cans and containers up to 10L
 <b>HDPE5305B</b>	0,2	0,95	B	Blow moulding, bottles for chemicals and detergents max 50L, with good chemical resistance
 <b>HDPE6205B</b>	0,35	0,95	B	Blow moulding, cans and containers max 250L, with good chemical resistance

B – basic stabilization with antioxidants and halogen scavenger