

PP Grades

| Grade | MFI (g / 10 min) | Density (g / cm ³) | Additives | Applications |
|------------------------------------|------------------|--------------------------------|-----------|---|
| injection solutions PPJ500 | 5 | 0,91 | B | Injection moulding, general purpose items |
| injection solutions PPJ700 | 12 | 0,91 | B | Injection moulding, general purpose items |
| injection solutions PPJ800 | 16 | 0,91 | B | Injection moulding, general purpose items |
| injection solutions PPJ900 | 20 | 0,91 | B | Injection moulding, general purpose items |
| injection solutions PPJ1000 | 24 | 0,91 | B | Injection moulding, general purpose items with thin walls |
| injection solutions PPJ1100 | 28 | 0,91 | B | Injection moulding, general purpose items with thin walls |
| injection solutions PPJ1200 | 32 | 0,91 | B | Injection moulding, general purpose items with thin walls |
| injection solutions PPJ1300 | 36 | 0,91 | B | Injection moulding, general purpose items with thin walls |
| injection solutions PPJ1400 | 40 | 0,91 | B | Injection moulding, general purpose items with thin walls |

HDPE Grades

| Grade | MFI (g / 10 min) | Density (g / cm ³) | Additives | Applications |
|--|------------------|--------------------------------|-----------|--|
| injection solutions HDPE2200J | 5 | 0,96 | B | Injection moulding, crates, automotive parts |
| injection solutions HDPE2208J | 5 | 0,96 | B, UV | Injection moulding, crates, automotive parts |
| injection solutions HDPERBI 8.0 | 8 | 0,95 | B | Injection moulding, housewares items, toys. |

B – basic stabilization with antioxidants and halogen scavenger
 UV – UV stabilizer